

Mupine Copper Corporation (MCC) – Production Report 2024

Period covered: May to December 2024.

This report summarises MCC's production performance for the second half of 2024.

Highlights (May–Dec 2024)

- Copper cathode production (metal recovered): 3,095.50 t.
- Average head grade (teneur alimentée): 1.30 %.
- Average metallurgical recovery (rendement): 85.00 %.
- Cathode purity: 99.998 %.

Monthly Production Summary

Month (2024)	Ore processed (t)	Metal recovered – cathodes (t)	Notes
Mai	7,558	101.43	
Juin	47,647	472.71	
Juillet	30,033	351.51	
Aout	30,460	424.75	
Septembre	30,314	197.88	
Octobre	46,903	513.31	
Novembre	45,020	514.72	
Décembre	50,855	519.19	

Inventory (Cathodes) – Stocks

Opening stock (May 2024): 0.000 t; Closing stock (December 2024): 1,041.283 t.

Charts

Monthly copper cathodes (metal recovered):

