

Mupine Copper Corporation (MCC) – Production Report 2025

Period covered: January to July 2025

This report summarises MCC's year-to-date operational performance.

Highlights

- Own-sourced copper cathode production (metal recovered, H1): 2,897.72 t.
- Average head grade (teneur alimentée): 1.22 %.
- Average metallurgical recovery (rendement): 84.67 %.
- Cathode purity (H1): 99.998 %.

Monthly Production Summary

MONTH (2025)	ORE PROCESSED (T)	METAL RECOVERED – CATHODES (T)	NOTES
Janvier	50,749	433.94	
Fevrier	51,917	501.48	
Mars	48,544	452.65	
Avril	58,610	506.52	
Mai	49,043	497.34	
Juin	43,792	505.78	
Juillet	1,591	15.25	

Inventory (Cathodes) – Stocks

Opening stock (January 2025): 1,471.227 t; Closing stock (July 2025): 33.865 t.

Charts

Monthly copper cathodes (metal recovered):

